














Reflective Tape Properties

REFLECTIVE TAPE 	Backing		Domestic wash
XM-6007C Pro  Segmented Heat transfer Silver			

Care Instructions

	Wash	Machine Wash Warm, 60°C
	Bleach	Do not bleach
	Dry	Tumble Dry Low
	Dry-clean	Do not dry clean
	Iron	Iron at low temperature, 110°C

Method of Application

Please contact us for instructions or check our web-site.

Important Notice

Type of work environment, exposure conditions and maintenance have an impact on reflective performance. Please test each tape according to appropriate care instructions required for the garment.

High-visibility clothing made with reflective material should be maintained in good condition and inspected regularly for damage or deterioration.

Description

Segmented Silver heat transfer reflective trim with excellent retro-reflectivity. Features extra breathability due to segmented design. It is recommended to use for EN 20471 knit clothing to have safe, functional and comfortable workwear. By means of a heat press or by simple ironing you can add this reflective trim to workwear adding safety and style at work.

Product Construction

The performance of XM-6007C Pro goes along with its durability, providing high reflectivity after tens of washes. Initial reflectivity of the tape is very high for a segmented tape, $R=465 \text{ cd/lx}\cdot\text{m}^2$ and after 50 washes it is still relatively high, $R=170 \text{ cd/lx}\cdot\text{m}^2$. As soft-shell fabric stretching, XM-6007C Pro tape is easily stretching along with the fabric. The tape is applied by Heat Press or Iron-on to EN 20471 vests, jackets, pants and increases the visibility of workers.

Product Detailed Information

Material	100% Polyester
Finish	-
Colour	Silver
Industrial wash	-
Roll, Width	50 mm
Roll, Length	100 meters
Roll, Weight	1.55 kgs

Product Certifications

NFPA 2112	-
ANSI 107	50×60°C ISO 6330
CSA Z96 (Level 2)	50×60°C ISO 6330
EN 20471	100×60°C ISO 6330
EN 469	-
EN 15384	-
OEKO-TEX 100	Class 2
Certificate of Test	Satra (UK), UL (USA)

Shelf Life

Keep in cool dry place, with no direct sunlight. Use the product during 12 months from the date of purchase.