

Kellner-145

55% COTTON / 45% POLYESTER

145 GSM / Twill 2/1



Fabric name	Kellner-145
Fabric weight	145 gsm $\pm$ 3%
Composition	55% Cotton, 45% Polyester
Full width	150 cm
Weave	twill 2/1
Finishes	
Area of use	light working uniform
Washing instruction	

Physical properties

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	810	395
2	Tearing strength, N	ISO 13937-3:2000	20	21
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3%	3%
4	Abrasion Resistance	ISO 12947-2:2002	-	
5	Pilling Resistance	ISO 12945-2:2000	3-4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010	3	
	Colour change	ISO 105-C06:2010	4-5	
	Colour staining	ISO 105-C06:2010	3-4	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		3-4	
	Colour staining		3-4	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		3-4	
	Wet		2-3	
9	Colour Fastness To Light	ISO 105-B02:2013	>4	