

Poliflex-220

90% POLYESTER / 10% SPANDEX

220 GSM / PLAIN 1/1 (4way stretch)



Fabric name	Poliflex-220
Fabric weight	220 ± 5 gsm
Composition	90% Polyester, 10% Spandex
Full width	152 ± 2 cm
Weave	Plain 1/1
Finishes	WR
Area of use	Jackets, Trousers, Special Uniform
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	920	2000
2	Tearing strength, N	ISO 13937-3:2000	19	106
3	Dimensional Stability after 5x60°C washes	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 20 000	
5	Pilling Resistance after 2000 revol.	ISO 12945-2:2000	5	
6	Colour Fastness To Washing (cotton+polyester) 40°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	5	
	Colour staining to cotton	ISO 105-C06:2010	4	
	Colour staining to polyamide	ISO 105-C06:2010	2	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change			
	Colour staining			
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry			
	Wet			
9	Colour Fastness To Light	ISO 105-B02:2013	4	

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com

XM TEXTILES EUROPE

Darius ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos.Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Fano di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com