



Flame Retardant fabric for FR-clothing

ARTEX-210

93% M-ARAMID / 5% P-ARAMID / 2%AS
210 GSM / TWILL 2/1



Fabric name	Artex-210
Fabric weight	210 ± 5 gsm
Composition	93% M-Aramid, 5% P-Aramid, 2% AS
Full width	152 ± 1 cm
Weave	Twill 2/1
Finishes	-
Application	FR jackets, trousers and coveralls
Washing instruction	

FR & SPECIAL PROPERTIES

Flame retardant	EN ISO 11612 (A1, B1, C1, F1)	50×60°C ISO 6330
Electric arc	EN 61482-2	50×60°C ISO 6330
Antistatic	EN 1149-5 (1149-3 method 2)	50×60°C ISO 6330
Multi-Risk	EN 13034	5×60°C ISO 6330

PHYSICAL PROPERTIES

		warp	weft
Tensile strength, N	ISO 13934-1:1999	1900	770
Tearing strength, N	ISO 13937-2:2000	59	38
Dimensional Stability To Washing, max	ISO 5077	3%	
Abrasion Resistance	ISO 12947-2:1999	—	
Pilling Resistance	ISO 12945-2:2001	—	

COLOUR FASTNESS

			Light	Mid	Dark	Special
			Orange, Red Yellow	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Black
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	4-5	4-5	4-5	4
		Stain on Polyester	4-5	4-5	4-5	4
		Stain on Cotton	4	4-5	4-5	3-4
Rub Fastness	ISO 105-X12	Wet	3	3	3	2-3
		Dry	4	4	4	4
Light Fastness	ISO 105-B02		3	3-4	4	4

www.xmtextiles.com

XM TEXTILES EUROPE

Darius ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos. Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Viale della Mercanzia 195, Blocco 1A, Centergross
40050 Fano di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com