XM FireLine

Flame Retardant fabric for FR-clothing

DEVON-260

55% MODACRYLIC / 44% COTTON / 1% AS

260 GSM / TWILL 2/1



Fabric name	Devon-260
Fabric weight	260 ± 10 gsm
Composition	55% Modacrylic, 44% Cotton, 1% AS
Full width	152 ± 2 cm
Weave	Twill 2/1
Finishes	-
Application	FR-clothing
Washing instruction	

FR & SPECIAL PROPERTIES

Flame retardant	EN ISO 11612 (A1, A2, B1, C1, E3, F1)	50×60°C ISO 6330
	EN ISO 11611 (Class 1)	50×60°C ISO 6330
Electric arc	EN 61482-2 (APC 1)	50×60°C ISO 6330
Antistatic	EN 1149-5	50×60°C ISO 6330
Hi-Vis	EN ISO 20471 (HV Yellow)	50×60°C ISO 6330

PHYSICAL PROPERTIES

		warp	weft
Tensile strength, N	ISO 13934-1:1999	780	630
Tearing strength, N	ISO 13937-2:2000	17	16
Dimensional Stability To Washing, max	ISO 6330	≤3%	
Abrasion Resistance	ISO 12947-2:1999	N/A	
Pilling Resistance	ISO 12945-2:2001	N/A	

COLOUR FASTNESS

			Light	Mid	Dark	Special colors
			Yellow, Red	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Orange
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	n/a	n/a	n/a	4-5
		Stain on Polyester	n/a	n/a	n/a	4-5
Rub Fastness	ISO 105-X12:1995	Wet	n/a	n/a	n/a	4
		Dry	n/a	n/a	n/a	5
Light Fastness	ISO 105-B02		n/a	n/a	n/a	n/a

*** Tested in a non-accredited laboratory**. * N/A - not applicable.

www.xmtextiles.com

XM TEXTILES EUROPE
Dariaus ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA
Sos.Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL
Viale della Mercanzia 195, Blocco 1A, Centergross
40050 Funo di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com