



Oxford-80

100% POLYESTER

80 GSM / PLAIN 1/1



Fabric name	Oxford-80
Fabric weight	80 gsm ± 3%
Composition	100% Polyester
Full width	59"/ 150 cm
Weave	plain 1/1
Finishes	WR, PU
Application	rain coats and light workwear jackets
Washing instruction	

Physical properties

			warp	weft
1	Tensile strength, (kg)	ISO 13934-1:2013	829	545
2	Tearing strength, (kg)	ISO 13937-3:2000	32	29
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 10 000	
5	Pilling Resistance	ISO 12945-2:2000	3-4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour staining	ISO 105-C06:2010	4-5	
	Colour change	ISO 105-C06:2010	3-4	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4-5	
	Colour staining		4-5	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4-5	
	Wet		2-3	
9	Colour Fastness To Light	ISO 105-B02:2013	> 4	