




|                     |   |
|---------------------|---|
| Fabric name         | Oxford-95   |
| Fabric weight       | 95 gsm ± 3%   |
| Composition         | 100% Polyester  |
| Full width          | 59"/ 150 cm   |
| Weave               | plain   |
| Finishes            | WR, PU  |
| Application         | rain coats and light workwear jackets   |
| Washing instruction |  |

## Physical properties

|   |  |                  | warp     | weft |
|---|--|------------------|----------|------|
| 1 | Tensile strength, (kg)                                   | ISO 13934-1:2013 | 81       | 63   |
| 2 | Tearing strength, (kg)                                   | ISO 13937-3:2000 | 2724     | 2621 |
| 3 | Dimensional Stability To Washing, max.                   | ISO 6330:2000    | 3.0%     | 3.0% |
| 4 | Abrasion Resistance                                      | ISO 12947-2:2002 | > 10 000 |      |
| 5 | Pilling Resistance                                       | ISO 12945-2:2000 | 3-4      |      |
| 6 | Colour Fastness To Washing (cotton+polyester) 60°C, min. | ISO 105-C06:2010 |          |      |
|   | Colour staining  | ISO 105-C06:2010 | 4-5      |      |
|   | Colour change  | ISO 105-C06:2010 | 3-4      |      |
| 7 | Colour Fastness To Perspiration, min.                    | ISO 105-E04:2013 |          |      |
|   | Colour change  |                  | 4-5      |      |
|   | Colour staining  |                  | 4-5      |      |
| 8 | Colour Fastness To Rubbing, min.                         | ISO 105-X12:2001 |          |      |
|   | Dry  |                  | 4-5      |      |
|   | Wet  |                  | 2-3      |      |
| 9 | Colour Fastness To Light                                 | ISO 105-B02:2013 | > 4      |      |