


Prima-160 Stretch

53% COTTON / 44% POLYESTER / 3% SPANDEX
160 GSM / Twill 2/1



Fabric name	Prima-160 Stretch
Fabric weight	160 gsm ± 3%
Composition	53% Cotton, 44% Polyester, 3% Spandex
Full width	150 cm
Weave	twill 2/1
Finishes	Ultra Soft
Area of use	HoReCa uniform
Washing instruction	

Physical properties

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1100	310
2	Tearing strength, N	ISO 13937-3:2000	25	21
3	Dimensional Stability To Washing 60°C, max.	ISO 6330:2000	2.0%	2.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 20 000	
5	Pilling Resistance after 7000 revol.	ISO 12945-2:2000	4	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010	4-5	
	Colour change	ISO 105-C06:2010	4-5	
	Colour staining to cotton	ISO 105-C06:2010	4-5	
7	Colour staining to polyester	ISO 105-C06:2010	4	
	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4-5	
8	Colour staining		4-5	
	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4-5	
9	Wet		2	
	Colour Fastness To Light	ISO 105-B02:2013	4	