




| | |
|---------------------|---|
| Fabric name | Unitec-240 WR |
| Fabric weight | 240 gsm ± 3% |
| Composition | 65% Polyester 35% Cotton |
| Full width | 150 cm |
| Weave | twill 2/1 |
| Finishes | WR (Fluorocarbon C6) |
| Area of use | multi seasonal workwear |
| Washing instruction |  |

Physical properties

| | | | warp | weft |
|----|--|------------------|------------|------|
| 1 | Tensile strength, N | ISO 13934-1:2013 | 1300 | 800 |
| 2 | Tearing strength, N | ISO 13937-3:2000 | 40 | 40 |
| 3 | Dimensional Stability To Washing, max. | ISO 6330:2000 | 3.0% | 3.0% |
| 4 | Abrasion Resistance | ISO 12947-2:2002 | > 30 000 | |
| 5 | Pilling Resistance | ISO 12945-2:2000 | 4 | |
| 6 | Colour Fastness To Washing (cotton+polyester) 60°C, min. | ISO 105-C06:2010 | | |
| | Colour change | ISO 105-C06:2010 | 4-5 | |
| | Colour staining | ISO 105-C06:2010 | 3-4 | |
| 7 | Colour Fastness To Perspiration, min. | ISO 105-E04:2013 | | |
| | Colour change | | 4-5 | |
| | Colour staining | | 4-5 | |
| 8 | Colour Fastness To Rubbing, min. | ISO 105-X12:2001 | | |
| | Dry | | 3-4 | |
| | Wet | | 2-3 | |
| 9 | Colour Fastness To Light | ISO 105-B02:2013 | > 4 | |
| 10 | Water Repellent | ISO 4920:2012 | 60 | |
| | before washing | | 100 points | |
| | after 10 washes 60°C | | 70 points | |